

DESCRIPTION

Backing			NT	MK
Thickness	ISO 24 346	mm	2.25 ± 0.15	6.20 ± 0.30
Weight	ISO 23 997	kg/m ²	2.20 ± 0.15	3.65 ± 0.30
Roll width		cm	200 (-0 +1)	196 (-0 +1)
Roll length		lm	24	15

PERFORMANCE

Dimensional stability	ISO 23 999 ASTM D 1204	%	≤ 0.3	
Abrasion resistance	TABER ISO 9352	mg	≤ 300	
Slip resistance	DIN 51130		R10	R10
Indentation test	ISO 24 343-1	mm	≤ 0.2	≤ 1.0
Low temperature resistance	D 42 1235 A	°C	- 20	- 20
Thermal conductivity	ISO 22007-2	W / wK		0.089
Phonic Insulation	ISO 717/2	dB	ΔI = 5	ΔI = 22
Colour fastness	ISO 105 B02 ISO 4582/80 ASTM D 4459		≥ 7	
Fire resistance	FMVSS 302		Conform	
	ASTM E648	W/cm ²	Class 1	
	R118-2		Conform	
Resistance to chemicals	ISO 26 987	-	Unaffected by diluted acids and bases Unaffected by domestic products (excluding solvents for plasticized PVC)	